



Bulldog Abrasives Southern Africa (Pty) Ltd.

Ad: No. 4 Andries Street South, Wynberg, South Africa, 2090

Tel: +27 (0) 11 786 5991 Fax: +27 (11) 786-5996 Website: <https://bulldogabrasives.co.za>

PRODUCT DESCRIPTION baseless SWEA00(WJC102)

Acrylic glue is used as the substrate, which is composed of substrate and isolation membrane. It has the characteristics of aging resistance, weather resistance, temperature resistance and no glue residue. Generally widely used in leather, nameplate, stationery, electronics, accessories fixed, footwear, handicrafts, hooks, paste positioning and other purposes.

TYPICAL PHYSICAL PROPERTIES

PROPERTIES	METRIC	ENGLISH	TEST METHOD
Total Thickness	1mm (1000 μ m)	39.37 Mil	PSTC-133 / ASTM D 3652
Liner Thickness (PE)	0.10mm (100 μ m)	3.93 Mil	PSTC-133 / ASTM D 3652
Adhesion to Steel (Let sit for 20min)	22N/25mm	79.16Oz/In.	PSTC-101 / ASTM D 3330
Adhesion to Steel (Let sit for 24H)	27N/25mm	97.15Oz/In.	PSTC-101 / ASTM D 3330
Holding Power 2.5cm*2.5cm*1kg*23°C	24H	24H	PSTC-107 / ASTM D 3654
Holding Power 2.5cm*2.5cm*0.25kg*80°C	72H	72H	PSTC-107 / ASTM D 3654
Holding Power 2.5cm*2.5cm*0.1kg*120°C	4H	4H	PSTC-107 / ASTM D 3654
Applying Temperature	+10 ~ 40 °C	+50 ~ +105 °F	-----
Service Temperature	-20 ~ +120 °C	-4 ~ +248°F	-----

PRODUCT FORM & SIZE AVAILABLE

umbo Roll: 800mm x 50m

IMPORTANT NOTE

1. The data above are typical values only, and should not be used for specifications purpose.
2. Tolerance: Thickness: $\pm 10\%$, Width: $\pm 1\text{mm}$; Length: Cut Roll: $\pm 0.3\text{m}$, Jumbo Roll $\pm 0.5\%$.

STORAGE & SHELF LIFE: 12 months when stored at $23\pm 2^\circ\text{C}$ (73°F) / 50% relative humidity out of direct sunlight.

SURFACE PREPARATION: It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied must be clean, dry, free of grease, oil or other contaminants.2024-1-18